

Press instruction Dimix DTF transfers

You will receive the pressing instructions for pressing from The Dimix Transfer-Jet and Powder-Fix DTF transfers.

Press Settings

- 130 degrees , 12 seconds for polyester
- 135 degrees , 12 seconds before o . a . cotton and cotton/polyester 50/50
- pressure of 4 bar / medium pressure
- cold peel : imitate 3 seconds if desired
- hot play : imitating 3 seconds is strongly advised

Wash resistance

- 40-60°C washable for at least 40 washes
- Inner butien Wash
- Do not iron and not in the dryer

More information: www.dimix.com/transferjet
Book a demo: showroom@dimix.com